

DATA SHEETMATERIAL REFERENCE – FLUORINOID® FL 108DESCRIPTION GLASS FIBRE FILLED PTFETYPICAL APPLICATIONS

Glass fibre is the most commonly used filler for sealing applications. It gives improved compression and wear properties.

This material may be inert gas sintered to further improve creep properties and reduce porosity and gas permeability. There will be a consequent loss of tensile properties.

TYPICAL PHYSICAL PROPERTIES #

| | | |
|-----------------------------|---------------------|-------------|
| SPECIFIC GRAVITY | (BS EN ISO 13000-2) | 2.18 – 2.30 |
| TENSILE STRENGTH | (BS EN ISO 13000-2) | 9 - 18 MPa |
| ELONGATION | (BS EN ISO 13000-2) | 100 - 200 % |
| SHORE D HARDNESS | (BS EN ISO 13000-2) | 64 - 76 |
| MAXIMUM WORKING TEMPERATURE | | 260°C |

These figures are typical values for the material and do not represent a product specification. Properties will vary depending on the source of raw material, method of processing, physical form of the product, direction of measurement etc.