



DATA SHEET

MATERIAL REFERENCE – FLUORONOID® FL010

DESCRIPTION VIRGIN PTFE

Material approved in accordance with **NORSOK M-710** Annex C, by Element Materials Technology Report No. C3014-1

TYPICAL APPLICATIONS

PTFE has a wide range of applications that make use of its extreme chemical resistance, very low coefficient of friction, excellent electrical insulation properties and thermal stability up to 260°C.

TYPICAL PHYSICAL PROPERTIES

Rod and tube can be compression moulded and will normally satisfy Grade 1. Material can be certified as satisfying these grades for a small extra cost (if required).

Properties	Unit	Grade 1	Grade 2
Density	g / cm ³	2.13 – 2.19	
Tensile Strength	MPa	>25	>20
Elongation	%	>280	>200
Hardness	ShoreD	55-65	

Properties determined in accordance with BS EN ISO 13000-2

NORSOK DATA SHEET

Fluorocarbon Company Ltd
Caxton Hill, Hertford, Herts
SG13 7NH, UK

Tel: +44 (0)1992 550731

Fax: +44 (0)1992 584697

Email: info@fluorocarbon.co.uk

Web: www.fluorocarbon.co.uk

Fluorinoid® is a registered trademark of Fluorocarbon Company Ltd, Caxton Hill, Hertford, Herts, SG13 7NH

TEST CERTIFICATE

This document certifies that

FL010 PTFE

from

FLUOROCARBON

meets the requirements of

NORSOK M-710 Rev. 2 in respect of sour fluid resistance

Test fluid: 2% hydrogen sulphide/hydrocarbon oil/water

Test pressure: 100 bar (10 MPa)

Passed by: Jeanne BABALOLA

Date: 16th September 2013

Element verify that machined tensile specimens of FL010 PTFE supplied by FLUOROCARBON have been exposed in a multi-phase sour fluid at three elevated temperatures.

Test Conditions

Exposure fluid composition and distribution

Volume (%)	Composition
30	2/3/95 mol% H ₂ S/CO ₂ /CH ₄
10	Distilled water
60	70% heptane, 20% cyclohexane, 10% toluene

The FL010 PTFE testpieces were placed in the hydrocarbon liquid phase for each exposure test.

Test temperatures and sampling intervals used in the NORSOK M-710¹ programme are shown in the table below; test pressure was 100 bar.

Exposure test conditions

Temperature (°C)	Intervals (days)
190	5, 10, 20, 50
205	5, 10, 20, 35
220	5, 10, 20, 35

Summary for FL010 PTFE

Swell¹	Tensile modulus²	Tensile strength²	Elongation at break²	NORSOK acceptable
PASS	PASS	PASS	PASS	YES

¹ <5% overall

² changes within ±50% range, from as-received level

FL010 PTFE behaved as expected when immersed in a liquid hydrocarbon oil phase with H₂S gas present: the material absorbed a small quantity of liquid early in the exposure period and this caused moderate reductions in tensile modulus and break property levels. The changes in room temperature tensile property levels are within the allowable range after exposure periods at 190-220 °C of up to 7 weeks. All exposed specimens were intact and there was no evidence that FL010 had been chemically aged by the conditions.

FL010 PTFE meets the requirements of the NORSOK M-710 Rev. 2 standard for sour fluid exposure.

¹ NORSOK M-710, "Qualification of non-metallic sealing materials and manufacturers", Rev. 2, October 2001